

Features

Anti-Bacteria Treated
Low Wick

Self-Clean
UV Resistant

Flame Retardant
Light Fastness

Applications



Technical Data Sheet

Item Code		I201	Test Method
Base Fabric		1000D*1000D 30*30	DIN EN ISO2060
Weight (GSM)		1450	DIN EN ISO2286-2
Tensile Strength	Warp (N/5cm)	4000	DIN53354
	Weft (N/5cm)	3800	DIN53354
Tear Strength	Warp (N/5cm)	600	DIN53363
	Weft (N/5cm)	500	DIN53363
Peeling Strength	Warp (N/5cm)	100	DIN53357
	Weft (N/5cm)	100	DIN53357
Temperature		-30°C/+70°C	
Flame Retardant		B1/M1/M2/NFPA701	
Lacquering (Optional)		Acrylic/ PVDF	
Special Treatment		Anti-Wicking/Anti-UV/Anti-Aging/Cold Resistant/Osmosis Prevention/Mildew Resistant	

Information contained in this document is based on our general experience and is given in good faith. But we are unable to accept responsibility in respect to factors which are outside our knowledge or control.



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat: +86-15858322153
mailto:hncomax@163.com jeffcheung@hncomax.com



Features

Anti-Bacteria Treated
Low Wick

Self-Clean
UV Resistant

Flame Retardant
Light Fastness

Applications



Technical Data Sheet

Item Code		I202	Test Method
Base Fabric		1000D*1000D 23*23	DIN EN ISO2060
Weight (GSM)		850	DIN EN ISO2286-2
Tensile Strength	Warp (N/5cm)	3100	DIN53354
	Weft (N/5cm)	2800	DIN53354
Tear Strength	Warp (N/5cm)	420	DIN53363
	Weft (N/5cm)	400	DIN53363
Peeling Strength	Warp (N/5cm)	100	DIN53357
	Weft (N/5cm)	100	DIN53357
Temperature		-30°C/+70°C	
Flame Retardant		B1/M1/M2/NFPA701	
Lacquering (Optional)		Acrylic/ PVDF	
Special Treatment		Anti-Wicking/Anti-UV/Anti-Aging/Cold Resistant/Osmosis Prevention/Mildew Resistant	

Information contained in this document is based on our general experience and is given in good faith. But we are unable to accept responsibility in respect to factors which are outside our knowledge or control.



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat: +86-15858322153
mailto:hncomax@163.com jeffcheung@hncomax.com



Features

Anti-Bacteria Treated
Low Wick

Self-Clean
UV Resistant

Flame Retardant
Light Fastness

Applications



Technical Data Sheet

Item Code		I203	Test Method
Base Fabric		1000D*1000D 23*23	DIN EN ISO2060
Weight (GSM)		750	DIN EN ISO2286-2
Tensile Strength	Warp (N/5cm)	2500	DIN53354
	Weft (N/5cm)	2300	DIN53354
Tear Strength	Warp (N/5cm)	350	DIN53363
	Weft (N/5cm)	300	DIN53363
Peeling Strength	Warp (N/5cm)	100	DIN53357
	Weft (N/5cm)	100	DIN53357
Temperature		-30°C/+70°C	
Flame Retardant		B1/M1/M2/NFPA701	
Lacquering (Optional)		Acrylic/ PVDF	
Special Treatment		Anti-Wicking/Anti-UV/Anti-Aging/Cold Resistant/Osmosis Prevention/Mildew Resistant	

Information contained in this document is based on our general experience and is given in good faith. But we are unable to accept responsibility in respect to factors which are outside our knowledge or control.



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat: +86-15858322153
mailto:hncomax@163.com jeffcheung@hncomax.com



Features

Anti-Bacteria Treated
Low Wick

Self-Clean
UV Resistant

Flame Retardant
Light Fastness

Applications



Technical Data Sheet

Item Code		I204	Test Method
Base Fabric		1000D*1000D 23*23	DIN EN ISO2060
Weight (GSM)		650	DIN EN ISO2286-2
Tensile Strength	Warp (N/5cm)	2500	DIN53354
	Weft (N/5cm)	2300	DIN53354
Tear Strength	Warp (N/5cm)	350	DIN53363
	Weft (N/5cm)	300	DIN53363
Peeling Strength	Warp (N/5cm)	100	DIN53357
	Weft (N/5cm)	100	DIN53357
Temperature		-30°C/+70°C	
Flame Retardant		B1/M1/M2/NFPA701	
Lacquering (Optional)		Acrylic/ PVDF	
Special Treatment		Anti-Wicking/Anti-UV/Anti-Aging/Cold Resistant/Osmosis Prevention/Mildew Resistant	

Information contained in this document is based on our general experience and is given in good faith. But we are unable to accept responsibility in respect to factors which are outside our knowledge or control.



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat: +86-15858322153
mailto:hncomax@163.com jeffcheung@hncomax.com

